

Böttcher compounds for Flexo sleeves

	Compound	Abrasion resistance	Polymer	Antistatic	Water based inks	Solvent based inks	UV based inks
	750 40 **	good	EPDM	yes	yes*	yes	yes
	731 50 **	good	EPDM	no	yes*	yes	yes
	751 50	very good	EPDM	yes	yes*	yes	yes
	735 60	very good	EPDM	no	yes*	yes	yes
	732 60	very good	EPDM	yes	yes*	yes	yes
	745 65	very good	EPDM	no	yes*	yes	yes
	756 65	very good	EPDM	yes	yes*	yes	yes
	746 70	very good	EPDM	yes	yes*	yes	yes
	757 70	very good	EPDM	yes	yes*	yes	yes
	758 80	very good	EPDM	yes	yes*	yes	yes
	749 90**	very good	EPDM	yes	yes*	yes	yes
	055 60 **	very good	SBR	yes	yes	no	no
	789 65	good	SBR	no	yes	If less than approx. 15% content of Ethyl acetate.	A chemical resistance test could be necessary.
	787 65	very good	SBR	yes	yes		
	045 80D **	very good	SBR	Compound for embossing			
	046 80D **	very good	SBR	Compound for embossing			

* Mineral oil based defoamer in water based inks can effect partial swelling on EPDM based compounds.

** This is not a standard Flexo compound, please consider a longer delivery time due to special mixing.